

J.L. VICENTIZ, S.L.
SUMINISTROS CERAMICOS

Bº Ugarte, s/n. - Pabellón 1 - Nave 10 - 48110 GATIKA (Bizkaia)
Tlf. 94-6156599 / 94-6156749 - FAX. 94-6155884 - e-mail: vicentiz@vicentiz.com



PUNTOS MEDIOS DE CAIDA DE LOS CONOS PIROMETRICOS HPC.

(Velocidad de calentamiento 150 °C/H.)

CONO Nº	TEMP. APROX. °C
---------	-----------------

022	600
021	650
020	670
019	690
018	710
017	730
016	750
015 a	790
014 a	815
013 a	835
012 a	855
011 a	880
010 a	900
09 a	920
08 a	940
07 a	960
06 a	980
05 a	1.000
04 a	1.020
03 a	1.040
02 a	1.060
01 a	1.080
1 a	1.100
2 a	1.120
3 a	1.140
4 a	1.160
5 a	1.180
6 a	1.200
7	1.230
8	1.250

CONO Nº	TEMP. APROX. °C
---------	-----------------

9	1.280
10	1.300
11	1.320
12	1.350
13	1.380
14	1.410
15	1.435
16	1.460
17	1.480
18	1.500
19	1.520
20	1.530
26	1.580
27	1.610
28	1.630
29	1.650
30	1.670
31	1.690
32	1.710
33	1.730
34	1.750
35	1.770
36	1.790
37	1.825
38	1.850
39	1.880
40	1.920
41	1.960
42	2.000